



Exposeal UW

Epoxy resin based putty for underwater repairs

Uses

For filling of blow holes, sealing of cracks underwater grouting, eliminating minor irregularities on concrete surfaces in damp and underwater conditions.

Advantages

- Easy mixing of base and hardener in 1:1 by weight
- Easy to apply and finish
- Non-slump, can be applied to vertical surfaces
- Chemical resistant
- Good adhesion to damp concrete
- Cures in submerged conditions without shrinkage

Description

Exposeal UW is a thixotropic, solvent free, two component compound based on water insensitive epoxy resins, inert fillers and thixotropic agents designed for applying in damp and submerged conditions. It is applied directly to concrete for filling cracks, blow holes etc., which cures to form a strong seal.

Technical Support

Fosroc provides a technical advisory service supported by a team of specialists in the field.

Properties

Mixed density	1.70 -1.80 g/cc
Volume solids	100%
Minimum application temperature	10°C
Compressive strength	25 N/mm ² on full cure
Pot life	30 min. at 30°C
Drying time	16 hrs at 30°C
Full cure	7 days at 30°C
Pressure resistance	More than 0.5 N/mm ² after 7 days

Application instructions

Surface preparation

Concrete surfaces should be clean and free from moss, algae, fungi etc. Wire brushing or abrading may be necessary to achieve suitable surface for application.

Mixing

Transfer the base and hardener component at 1:1 ratio into a suitable container. Using a heavy duty, slow speed drill fitted with a suitable mixing paddle, mix the two components to achieve a uniform consistency. It is important that both the components are intermixed thoroughly.

Application

Due to its easy workability the product can be applied by using a scraper, filling knife or by manual means. After complete mixing, the material can be used directly from the Can or subdivided on to the spot boards for individual applications.

Tool cleaning

The tools should be cleaned after use before the material cures. Nitoflor Sol shall be used for cleaning the tools. Cured material can only be removed mechanically.

Limitations

Exposeal UW is not suitable for application below 10°C and above 40°C.

Cured Exposeal UW is not suitable for subzero temperatures.

Estimating

Packaging

Exposeal UW	2.4 and 24 litre packs
Nitoflor Sol	5 litre & 20 litre cans

Coverage

Exposeal UW will be consumed at a rate of 1m² at 1mm thickness/Litre. Depending on the substrate conditions the coverage may vary.

Storage

Shelf Life

12 months in unopened containers when stored under normal warehouse conditions.

Exposeal UW

Precautions

Health & Safety instructions

Contact with the skin and eye should be avoided. Gloves, goggles and masks should be worn during application.

If the product comes in contact with the skin, it should be washed thoroughly with a suitable industrial cleaner with luke warm water and soap. In case of eye contact, should be washed with clean water and medical advice should be sought immediately.

The material should not be exposed to naked flame. Smoking is prohibited during handling /application of the product.

Fire

Exposeal UW base and hardener are nonflammable. Nitoflor Sol is flammable. Do not use near naked flames. No smoking.

Additional information

The Fosroc range of associated products includes high strength cementitious grouts, epoxy injection systems and grouts, polyester resin based mortar for rapid presetting of steel shims to level or for direct bedding of small base plates; resin anchoring systems for same day anchoring of bolts in drilled holes in concrete or rock. Also available a range of products for use in construction viz. admixtures, curing compounds, mould release agents, flooring systems and repair mortars.

Separate datasheets are available on these products.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028,
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

Shrachi Tower, Wing A, 3rd
floor, Anandapur Em Bypass
Anandapur, Kolkata
West Bengal 700 107
Ph: +91 8420985630
Fax: 033-24990278