



# Conbextra HES

## Free flow, high strength, rapid setting, cementitious grout

### Uses

Conbextra HES is used for special grouting where it is essential to have fast setting and high early strength. It can also be used for grouting/fixing glass or metallic railings in concrete.

### Advantages

- Non-shrink
- Quick setting
- No metallic ion content to cause staining
- Pre-packed material overcomes onsite batching variations
- Develops high early strength without the use of chlorides
- High ultimate strength and low permeability ensure the durability of the hardened grout
- Free flow ensures high level of contact with load bearing area

### Description

Conbextra HES is supplied as a ready to use dry powder. The addition of a controlled amount of clean water produces a free flowing, non-shrink grout for gap thicknesses up to 50mm.

Conbextra HES is a blend of Portland cement, graded fillers and chemical additives which impart non shrink property whilst minimising water demand. The formulation ensures high early strength. The graded filler is designed to assist uniform mixing and produce a consistent grout.

### Technical support

An experienced technical advisory team is available to give technical service on request.

### Properties

Setting time at 27°C (IS 5513)

Initial	11 - 14 minutes
Final	15 - 17 minutes

Compressive strength : (BS 1881:Part 116)

Age (days)	Compressive strength (N/mm <sup>2</sup> )	
	Pourable consistency( W/P 0.21)	
1 hr	15	
3 hr	20	
6 hr	25	
24 hr	30	
3 days	40	
7 days	48	
28 days	55	

Age (days)	Flexural strength ( BS 4551) (N/mm <sup>2</sup> )	Tensile strength (N/mm <sup>2</sup> )
1	4.05	1.2
3	4.20	1.8
7	4.60	3.0
28	5.00	4.0

Pullout bond strength (W/P 0.21)	17N/mm <sup>2</sup> @ 7 days 20N/mm <sup>2</sup> @ 28 days
----------------------------------	---

Freshwet density	1.98 - 2.01 g/cc
------------------	------------------

**Note:** The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing of field-applied samples may vary, depending on actual site conditions.

### Application instructions

#### Surface Preparation

#### Foundation surface

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitence, it must be cut back to a sound base. Bolt holes and fixing pockets must be blown clean of any dirt or debris.

#### Pre-soaking

Several hours prior to placing, the concrete substrates should be saturated with fresh water.

Immediately before grouting takes place any free water should be removed with particular care being taken to blow out all bolt holes and pockets.

# Conbextra HES

---

## Formwork

The formwork should be constructed to be leakproof. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints.

In some cases it is practical to use a sacrificial semi-dry sand and cement formwork. The formwork should include outlets for pre-soaking.

## Unrestrained surface area

This must be kept to a minimum. Generally the gap width between the perimeter formwork and the plate edge should not exceed 150mm on the pouring side and 50mm on the opposite side. It is advisable, where practical, to have no gap at the flank sides.

## Mixing and placing

### Mixing

For best results a mechanically powered grout mixer should be used. When quantities up to 30kg are used, a slow speed drill fitted with a high shear mixer is suitable.

To enable the grouting operation to be carried out continuously, it is essential that sufficient mixing capacity and labour are available. The use of a grout holding tank with provision to gently agitate the grout may be required.

**Note :** When required to grout at high ambient temperatures, Fosroc recommends usage of cold water maintained at 5°C.

## Consistency of grout mix

The quantity of clean water required to be added to a 15kg bag to achieve the desired consistency is given below

The selected water content should be accurately measured into the mixer. The total content of the Conbextra HES bag should be slowly added and continuous mixing should take place for 5 minutes. This will ensure that the grout has a smooth even consistency.

## Placing

At 30°C place the grout within 10 minutes of mixing.

Conbextra HES can be placed in thicknesses up to 50mm in a single pour.

For thicker sections it is necessary to fill out Conbextra HES with well graded silt free aggregate to minimise heat build up. Typically a 5 - 10mm aggregate is suitable. 50 - 100% aggregate weight of Conbextra HES can be added depending on the

thickness to be applied.

Continuous grout flow is essential. Sufficient grout must be prepared before starting. The time taken to pour a batch must be regulated to the time to prepare the next one.

The uniformly mixed grout should be placed using a suitable grout pump for faster application.

## Curing

On completion of the grouting operation, the grout should be left for air drying. However membrane curing agent or polythene sheet may be used to give an early surface protection from precipitation. But never cure the grout with water.

## Cleaning

Conbextra HES should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically, or with Reebaklens.

## Limitations

### Low temperature working

When the air or contact surface temperatures are 10°C or below on a falling thermometer, the strength development may be slow.

Normal precautions for winter working with cementitious materials should then be adopted.

### High temperature working

At ambient temperatures above 35° C, cool water ( below 20°C) should be used for mixing the grout prior to placement. Otherwise the pot life of the mixed material will be reduced.

## Estimating

### Packaging

Conbextra HES is supplied in 15 kg moisture resistant bags.

### Yield

Allowance should be made for wastage when estimating quantities required. The approximate yield per 15 kg bag is 9 litres ( for pourable consistency).

## Storage

### Shelf life

Conbextra HES has a shelf life of 6 months if kept in a dry store in sealed bags. If stored in high temperature and high humidity locations, the shelf life may be reduced.



# Conbextra HES

---

## Precautions

### Health and Safety

Conbextra HES is alkaline and should not come into contact with skin and eyes. Avoid inhalation of dust during mixing.

Gloves, goggles and dust mask should be worn.

If contact with skin occurs, wash with water. Splashes to eyes should be washed immediately with plenty of clean water and medical advice sought.

### Additional information

Fosroc manufactures a wide range of products specifically designed for the repair and refurbishment of damaged reinforced concrete. This includes repair mortars, fluid microconcretes, chemical resistant epoxy mortars in addition to comprehensive package of protective coatings. In addition, a wide range of complementary products are available. This includes joint sealants, waterproofing membranes, grouts and anchors and specialised flooring materials.

\*Separate data sheets are available on these products.



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

Embassy Point, No. 150,  
2nd Floor, Infantry Road,  
Bangalore 560 001,  
Karnataka

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

+91 80-42521900

### fax

+91 80-22281510

### e-mail

enquiry.india@fosroc.com

### Regional Offices

#### Chennai

Hills Centre, Old No 5,  
New No 9, 3rd Cross Street,  
Jeth Nagar, Raja Annamalaipuram,  
Chennai 600 028.  
Ph: 9500064795

#### Mumbai

MBC Park, 12th floor, Office No.12B,  
'D' Block, Near G Corp/Hyper City  
Kasarwadawali, Ghodbunder Road,  
Thane (West) 400 615  
Ph: +91 22 6229 6800

#### Noida

Unit No. 601, Highway Tower-II  
A-13/2, 6th Floor, Sector-62  
Gautam Buddha Nagar,  
Noida 201 309, Uttar Pradesh  
Ph: +91 120 6121900  
Fax: 0120-4270622

#### Kolkata

304, Jodhpur Park  
Kolkata 700 068  
Ph: +91 33-65343188  
Fax: 033-2499-0278